

ATTACHMENT C  
NEWLY ADDED CLAIMS

7. (New) The method of claim 6 wherein the non-charging resin composite material has a ratio of the surface resistance of the resin composite material to the resistivity of the component containing metal element of  $10^{12}$  to  $10^{17}$  ( $1/\square \cdot \text{cm}$ ).

A2  
8. (New) The method of claim 6 wherein the non-charging composite material has a surface resistance of  $10^6$  to  $10^{11}$   $\Omega/\square$ .

9. (New) The method of claim 6 wherein the resin base is selected from the group consisting of epoxy resin, polyimide resin, vinyl resin, phenol resin, nylon resin, polyphenylene ether resin, polypropylene resin, fluorine-based resin, ABS resin and mixtures thereof.

10. (New) The method of claim 6 wherein the metal element is selected from the group consisting of V, Cr, Mn, Fe, Co, Ni, Cu, Ga, As, Se, Mo, Ru, Rh, Pd, Ag, Cd, In, Sb, Te, Os, Ir, Pt, Au, Hg, Pb, Bi and mixtures thereof.

11. (New) The method of claim 6 wherein the component containing metal element is selected from the group consisting of metals, metal arsenides, metal antimonides, metal selenides, metal tellurides, metal sulfides and metal oxides.

20140501 E6T0T00T